

EUROPEAN PATENT OFFICE

Patent Abstracts of Japan

PUBLICATION NUMBER : 01007475
PUBLICATION DATE : 11-01-89


APPLICATION DATE : 30-06-87
APPLICATION NUMBER : 62161060

APPLICANT : MITSUBISHI HEAVY IND LTD;

INVENTOR : IRINO MITSUHIRO;

INT.CL. : H01M 8/02 H01M 8/12

TITLE : MANUFACTURE OF FLAT TYPE SOLID
ELECTROLYTE FUEL CELL



ABSTRACT : PURPOSE: To prevent cracks in the laminated body of a fuel cell in the title at the time of drying and baking by mixing fibers of yttria stabilized zirconia in the first slurry, and mixing LaCaCrO_3 , LaMgCrO_3 or Al_2O_3 , and yttria stabilized zirconia fibers in the second slurry.

CONSTITUTION: In the process of laminating a solid electrolyte film 1 consisting of the first slurry, an oxygen side electrode film 2, a fuel side electrode film 3, and an interconnector 4 consisting of the second slurry, and drying and baking the laminated body, yttria stabilized zirconia fibers 5 are mixed in the first slurry, and LaCaCrO_3 , LaMgCrO_3 or Al_2O_3 , and yttria stabilized zirconia fibers 6 are mixed in the second slurry. This improves strength of the solid electrolyte film and interconnector, thereby occurrence on cracks in the laminated body to cause it to be split can be prevented at the time of drying and baking.

COPYRIGHT: (C)1989,JPO&Japio